







Technical data sheet

PET-GAG Type 340 CARD-LAMINATION-FILMS

Configuration 	
outside layers	PET-G virgin resin, antiblock
middle layers	< 40% Recyclat
Dimension 	
nominal thickness value (mechanical)	0.080 ... 0.150 mm
nominal size value	≤ 700 x 1200 mm
Tolerance	see General Terms & Conditions
Physical properties 	
Color	Colorless translucent
Specific gravity	1,32 g/cm ³
Softening point	71° C
Surface Tension	≥ 38 dyn/cm
Impact Strength	≥ 250 kJ/m ²
Tensile Strength	≥ 45 N/mm ²
Field of application 	
Printing	Silk-Screen
Lamination	suitable

The product is in accordance with the regulations of:

- Commission Regulation EU 10/2011
- BfR Recommendation XVII and Consumer Goods Regulations, Civil Code, Part I, No. 23.94, pages 775 and following;
- FDA, Title 21 Part 177.1630 and supplementary regulation 21 CFR 177, 1315(b)(1)(USA).

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

DATASHEET PET-GAG Film Type 340 CARD-AMINATION-FILMS

Valid from 2016-02-01 until further notice

