





Technical data sheet**PET-G FILM TYPE 299 FORMING FILMS**

Configuration		
outside layers	PET recyclat blue-tinted, antiblock-additive	
middle layers (type 299)	PET recyclat blue-tinted	
Dimension		
nominal thickness value	0.200 ... 0.800 mm	
nominal size value	≤ 1000 mm	
Tolerance	see General Terms & Conditions	
Physical properties		
Color	Cblue-tinted	
Density	1.27 g/cm ³	
Vicat softening point	71° C	
Shrinkage	≤ 10,0 % (10 min at 140°C, depending on film thickness)	
Field of application		
Forming	all kinds (Tool temperature ≥ 30 °C, Forming ≥ 120 °C)	

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

