






Technical data sheet**PET-MPE FILM TYPE 600 FORMING FILMS**

Configuration 	
outside layers	PET Copolyester, anti-blocking agents
middle layers (type 600)	100% PET Copolyester
Dimension 	
nominal thickness value	0.150 ... 0.800 mm
nominal size value	≤ 1200 mm
Tolerance	see General Terms & Conditions
Physical properties 	
Color	colorless transparent
Density	1.20 g/cm ³
Vicat softening point	110° C
Shrinkage	≤ 10 % (10 min at 140°C, depending on thickness)
Options on request 	
Color	specified color according reference
PE-protection film	one or both sides
UV-protection	UV light transmittance ($\lambda = 360 \text{ nm}$) ≤ 0,5 %
Flame retardant	UL 94 V2 or DIN 4102 B2 classification (tested on film thickness 200 μm)
Field of application 	
Forming	all kinds (Tool temperature ≥ 30 °C, Forming ≥ 120 °C)
Sealing, Welding	High-Frequency, Ultrasonic (depending on medium)
Sterilization	Gamma, ETO

The product is in accordance with the regulations of:

- Commission Regulation EU 10/2011
- BfR Recommendation XVII and Consumer Goods Regulations, Civil Code, Part I, No. 23.94, pages 775 and following;
- FDA, Title 21 Part 177.1630 and supplementary regulation 21 CFR 177, 1315(b)(1)(USA).

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

