





## Technical data sheet

## BIO-PET TYPE 926030 FORMING FILMS

<b>Configuration</b>	
Material	PET-A virgin resin (BIO-PET), anti-blocking agents
<b>Dimension</b>	
Nominal thickness value	0.150 ... 0.800 mm
Nominal size value	≤ 1200 mm
Tolerance	see General Terms & Conditions
<b>Physical properties</b>	
Color	colorless transparent
Density	1.33 g/cm <sup>3</sup>
Vicat softening point	71° C
Shrinkage	≤ 10,0 % (10 min at 140°C, depending on film thickness)
<b>Field of application</b>	
Forming	all kinds (tool temperature ≥ 30 °C, forming ≥ 120 °C)
Sealing, Welding	high-frequency, ultrasonic (depending on medium)

### The product is in accordance with the regulations of:

- Commission Regulation EU 10/2011
- BfR Recommendation XVII
- Raw materials comply to FDA, Title 21 Part 177.1630 and supplementary regulation 21 CFR 177, 1315(b)(I)(USA)

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

DATASHEET BIO-PET TYPE 96030 FORMING FILMS

Version 04. Valid from 2017-07-31 until further notice

**Folienwerk Wolfen GmbH**  
 Guardianstraße 4  
 06766 Bitterfeld-Wolfen  
 Germany

T +49 (0)3494 6979 0  
 F +49 (0)3494 6979 37  
 info@folienwerk-wolfen.de  
 www.folienwerk-wolfen.de

Amtsgericht Stendal, HRB 10684  
 Managing Director: Günther Burkardt  
 Authorized Representative: Thomas Olszowy  
 Ust.-ID: DE139739757

