






Technical data sheet

PET-A FILM TYPE 100 MEDICAL FILMS

Configuration 	
Outside layers	PET-A virgin resin, anti-blocking agents
Middle layers	PET-A virgin resin
Dimension 	
Nominal thickness value	0.150 ... 0.800 mm
Nominal size value	≤ 1,200 mm
Tolerance	see General Terms & Conditions
Physical properties 	
Color	colorless transparent
Density	1.33 g/cm ³
Vicat softening point	71 °C
Shrinkage	≤ 10 % (10 min at 140 °C, depending on film thickness)
Options on request 	
Color	specified color according reference
PE-protection film	one or both sides
UV-protection	UV light transmittance ($\lambda = 360 \text{ nm}$) ≤ 0.5 %
Antistatic treatment, external	on both sides surface resistance ≤ 10 ⁹ Ohm ¹⁾
Antistatic treatment, internal	on both sides surface resistance ≤ 10 ¹² Ohm ^{1), 2)}
Field of application 	
Forming	all kinds (tool temperature ≥ 30 °C, forming ≥ 120 °C)
Sealing, Welding	high-frequency, ultrasonic (depending on medium)

- 1) measured at 50 % relative humidity
 2) product currently under development

The product is in accordance with the regulations of:

- Commission Regulation EC 10/2011
- BfR Recommendation XVII
- Raw materials comply to FDA, Title 21 Part 177
- The used PET-A is biocompatible according to test conditions of US Pharmacopeia (USP) Class VI and ISO 10993

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

DATASHEET PET-A Film TYPE 100 MEDICAL FILMS

Version 06. Valid from 2018-01-16 until further notice

Folienwerk Wolfen GmbH
 Guardianstraße 4
 06766 Bitterfeld-Wolfen
 Germany

T +49 (0)3494 6979 0
 F +49 (0)3494 6979 37
 info@folienwerk-wolfen.de
 www.folienwerk-wolfen.de

Amtsgericht Stendal, HRB 10684
 Managing Director: Günther Burkardt
 Authorized Representative: Thomas Olszowy
 Ust.-ID: DE139739757

