






## Technical data sheet

## PET-GAG FILM TYPE 300 MEDICAL FILMS

<b>Configuration</b> 	
Outside layers	PET-G virgin granulate (Estar 6763); anti-blocking and slip agents
Middle layers (type 300)	PET-A virgin resin, blue-tinted available
<b>Dimension</b> 	
Nominal thickness value	0.150 ... 1.000 mm
Nominal size value	≤ 1,200 mm
Tolerance	see General Terms & Conditions
<b>Physical properties</b> 	
Color	colorless transparent
Density	1.32 g/cm <sup>3</sup>
Vicat softening point	71 °C
Shrinkage	≤ 10 % (10 min at 140 °C, depending on film thickness)
<b>Options on request</b> 	
Color	specified color according reference
PE-protection film	one or both sides
UV-protection	UV light transmittance ( $\lambda = 360 \text{ nm}$ ) ≤ 0.5 %
Antistatic treatment	on both sides surface resistance ≤ 10 <sup>9</sup> Ohm (measured at 50 % relative humidity)
<b>Field of application</b> 	
Forming	all kinds (tool temperature ≥ 30 °C, forming ≥ 120 °C)
Sealing, Welding	high-frequency, ultrasonic (depending on medium)
Sterilization	Gamma, ETO, E-Beam

### The product is in accordance with the regulations of:

- Commission Regulation EU 10/2011
- BfR Recommendation XVII
- Raw materials comply to FDA, Title 21 Part 177
- The used PET materials are biocompatible according to test conditions of US Pharmacopeia (USP) Class VI and ISO 10993

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a non-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

DATASHEET PET-GAG Film TYPE 300 MEDICAL FILMS

Version 05. Valid from 2017-10-18 until further notice

**Folienwerk Wolfen GmbH**  
 Guardianstraße 4  
 06766 Bitterfeld-Wolfen  
 Germany

T +49 (0)3494 6979 0  
 F +49 (0)3494 6979 37  
 info@folienwerk-wolfen.de  
 www.folienwerk-wolfen.de

Amtsgericht Stendal, HRB 10684  
 Managing Director: Günther Burkardt  
 Authorized Representative: Thomas Olszowy  
 Ust.-ID: DE139739757

