






Technical data sheet**PET-G FILM TYPE 299 PRINTING FILMS**

Configuration 	
outside layers	PET recyclat, antiblock-additives
middle layers (type 299)	PET recyclat
Dimension 	
nominal thickness value	0.200 ... 0.800 mm
nominal size value	≤ 1000 x 1400 mm
Tolerance	see General Terms & Conditions
Physical properties 	
Color	Blue-tinted
Density	1.27 g/cm ³
Vicat softening point	71° C
Surface tension	≥ 40 dyn/cm
Options on request 	
Corona treatment	one or both sides (increases the surface tension)
PE-protection film	one or both sides
UV-protection	UV light transmittance ($\lambda = 360 \text{ nm}$) ≤ 0,5 %
Field of application 	
Gluing, Stamping, Folding	all kinds
Printing	UV-Offset, Silk-Screen, Flexo

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

DATASHEET PET-G FILM TYPE 299 PRINTING FILMS

Valid from 2015-12-01 until further notice

