






Technical data sheet
**PET-GAG FILM TYPE 3XX FORMING FILMS,
 with BOPET laminated**

Configuration	
Outside layers	PET-G virgin resin, anti-blocking agents
Middle layers (type 300)	100% PET-A virgin resin
Middle layers (type 320)	< 20% recycled material
Middle layers (type 340)	< 40% recycled material
Outside laminate	Biaxially-oriented PET (BOPET) film, 12 µm thickness
<hr/>	
Dimension	
Nominal thickness value (mechanical)	0.150 ... 0.800 mm
Nominal size value	≤ 1,200 mm
Tolerance	see General Terms & Conditions
<hr/>	
Physical properties	
Color	colorless transparent
Density	approx. 1.32 g/cm ³
<hr/>	
Options on request	
Color	specified color according reference
<hr/>	
Field of application	
Forming	all kinds (tool temperature ≥ 30 °C, Forming ≥ 120 °C)
Sealing, Welding	high-frequency, Ultrasonic (depending on medium)

The product is in accordance with the regulations of:

- European Directive 2011/65/EC (RoHS)
- European Directive 1907/2006/EC (Reach)

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a non-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

