








Technical data sheet

ECO-R-PET FILMS TYPE 199 PRINTING FILMS

Configuration 	
Outside layers	PET-A post-consumer recycled material, evaluated by EFSA ¹⁾ , anti-blocking agents
Middle layers	PET-A post-consumer recycled material, evaluated by EFSA ¹⁾
Dimension 	
Nominal thickness value	0.150 ... 0.800 mm
Nominal size value	≤ 1,200 x 1,600 mm
Tolerance	See General Terms & Conditions
Physical properties 	
Color	colour-tinted transparent
Density	approx. 1.33 g/cm ³
Surface tension	≥ 38 dyn/cm
Options on request 	
Color	specific color according reference
Corona treatment	one or both sides (increases the surface tension)
PE-protection film	one or both sides
UV-protection	UV light transmittance ($\lambda = 360 \text{ nm}$) ≤ 0,5 %
Field of application 	
Gluing, Stamping, Folding	All kinds
Printing	UV-Offset, Silk-Screen, Flexo

The product is in accordance with the regulations of:

- Commission Regulation EU 10/2011
- BfR Recommendation XVII
- Raw materials comply to FDA, Title 21 Part 177.1630 and supplementary regulation 21 CFR 177, 1315(b)(I)(USA)

1) EFSA = European Food Safety Authority.

For the film type mentioned above, only post-consumer recycled material is used which is produced by a recycling process with a positive evaluation of the EFSA. This evaluation is according to the Commission regulation (EC) no. 282/2008 on recycled materials intended to come into contact with food.

All specified physical characteristics are indications. Deviations from the values given here are mostly due to technological reasons and not per se justifying the claim of the goods. All specified physical properties are only valid for a none-processed film. The assessment of the suitability of a film of FWG for the intended purpose is in customer's responsibility.

